

Nicotarp 7 Specification

TEST	UNIT	Nicotarp 7	TEST METHOD
Weight	g/m ²	190	NEN-EN 965
Thickness at 2kPa	mm	0.3	DIN 53370
Core material		HDPE	
Coating material		LDPE	
Tensile strength MD	N/5 cm	850	ISO 1421
Tensile strength CD	N/5 cm	850	ISO 1421
Elongation at break MD	%	30	ISO 1421
Elongation at break CD	%	20	ISO 1421
Tear resistance MD	N	250	ASTM D4533
Tear resistance CD	N	150	ASTM D4533
Length	m	100	
Width	m	2.0	
Diameter of roll	m	0.2	
Weight of roll	kg	39	

Nicotarp 7 “P”

is a micro-perforated version of the material which allows moisture vapour to escape whilst maintaining complete water tightness.

WaterVapourTransmission	g/m ² /day	55.6	Lyssy (DIN53122)
Resistamnce to water penetration	ml	0	prEN13111

Issue 3 - Jan08