

PAG Protective felt (325gsm)

PROPERTIES	MD/CD	UNIT	VALUE	STANDARD
Tensile strength	MD	kN/m	24.0	EN ISO 10319
	CD	kN/m	24.0	EN ISO 10319
Elongation at max. load	MD	%	100	EN ISO 10319
	CD	%	40	EN ISO 10319
Static Puncture (CBR)		N	3850	EN ISO 12236
Cone Drop test (hole dia.)		mm	17	EN ISO 13433
Permeability Vertical (dh=50mm)		l/m ² /s	60	EN ISO 11058
Opening size O ₉₀		micron	90	EN ISO 12956
Thickness	2kPa	mm	2.9	EN ISO 9863-1
Mass per unit area		g/m ²	325	EN ISO 9864
Roll size	Width	m	2/4	
	Length	m	100	

Issue 3 - Jan08