

PAG Cross Linked Butyl Sealant

PROPERTY	
Elongation at Break	220%
Force to Compress by 20%	220N
Movement accomodation	15%
Moisture Vapour Transmission Rate	0.24g/m ² /24Hrs
Density	1.6g/cm ²
Service Life (Predicted)	>20 Yrs
Service temperateure range	-4C to+110C
Shrinkage	<0.5%
Shear strength	17.1N
Roll size	30mm x 30m

PAG Cross Linked Butyl Sealant has good UV resistance, is mould resistant and has virtually no slump.

Issue3 - Jan08